



## SPECIFICATION

### THICK PALE CREPE - TPC 3

Average specifications - Thick Pale Crepe - TPC 3

Properties	Unit	*Avg Spec
Dirt Content - Max	% wt	0.05
Ash content - Max	% wt	0.4
Volatile Matter - Max	% wt	0.7
Nitrogen Content - Max	% wt	0.5
Initial Wallace Plasticity (PO)		40-60
Plasticity Retention Index (PRI)		50-65
Mooney Viscosity (ML, 1 + 4 at 100°C)		75-85
Lovibond Colour		1.5 - 3.5

Latex crepe is sold on visual grading.

\*These figures represents Average Specification. Actual parameters can differ.

Packing :

25 kg/Bale

Loose bales, Shrink Wrapped Wooden/Disposable Plastic Pallet, Metal box.