



SPECIFICATION

THICK PALE CREPE - TPC 4 MIX

Average specifications - Thick Pale Crepe - TPC 4 mix

Properties	Unit	*Avg Spec
Dirt Content - Max	% wt	0.6
Ash content - Max	% wt	0.5
Volatile Matter - Max	% wt	0.6
Nitrogen Content - Max	% wt	0.6
Initial Wallace Plasticity (PO)		40-60
Plasticity Retention Index (PRI)		60-80
Mooney Viscosity (ML, 1 + 4 at 100°C)		75-85
Lovibond Colour		4.5 - 7

Latex crepe is sold on visual grading.

*These figures represents Average Specification. Actual parameters can differ.

Packing :

25 kg/Bale

Loose bales, Shrink Wrapped Wooden/Disposable Plastic Pallet, Metal box.