



## SPECIFICATION

### THICK PALE CREPE - TPC 1X

#### Average specifications - Thick Pale Crepe - TPC 1X

| Properties                            | Unit | *Avg Spec |
|---------------------------------------|------|-----------|
| Dirt Content - Max                    | % wt | 0.02      |
| Ash content - Max                     | % wt | 0.2       |
| Volatile Matter - Max                 | % wt | 0.5       |
| Nitrogen Content - Max                | % wt | 0.35      |
| Initial Wallace Plasticity (PO)       |      | 40-60     |
| Plasticity Retention Index (PRI)      |      | 60-75     |
| Mooney Viscosity (ML, 1 + 4 at 100°C) |      | 75-85     |
| Lovibond Colour                       |      | 1 - 1.5   |

Latex crepe is sold on visual grading.

\*These figures represents Average Specification. Actual parameters can differ.

Packing :

25 kg/Bale

Loose bales, Shrink Wrapped Wooden/Disposable Plastic Pallet, Metal box.