



## SPECIFICATION

### THICK PALE CREPE - 3X BROWN CREPE

Average specifications - 3X Brown Crepe

Properties	Unit	*Avg Spec
Dirt Content - Max	% wt	0.3
Ash content - Max	% wt	0.8
Volatile Matter - Max	% wt	0.7
Nitrogen Content - Max	% wt	0.6
Initial Wallace Plasticity (PO)		35-55
Plasticity Retention Index (PRI)		45-60
Mooney Viscosity (ML, 1 + 4 at 100°C)		75-90
Lovibond Colour		7.5 - 9

Latex crepe is sold on visual grading.

\*These figures represents Average Specification. Actual parameters can differ.

Packing :

25 kg/Bale

Loose bales, Shrink Wrapped Wooden/Disposable Plastic Pallet, Metal box.