



SPECIFICATION

CONCENTRATED LATEX 60% DRC CHARACTERISTICS High Ammonia(HA)

Properties	Limit	*Avg Spec
Total Solids Content, %(m/m)	Min	61 or by an agreement between two parties
Dry Rubber Content, %(m/m)	Min	60.0
Non-Rubbers Solids, %(m/m)	Max	1.70
Alkalinity/ Latex Concentrate, %(m/m)	Min	0.60
Mechanical Stability Time (MST), s **	Min	650
Volatile fatty acid (VFA)	Max	0.06 or by an agreement between two parties
KOH number.	Max	0.7 or by an agreement between two parties
pH Value		-
Coagulum Content, %(m/m)	Max	0.03
Sludge content, %(m/m)	Max	0.10
Copper content (mg/kg)	Max	8
Manganese content (mg/kg)	Max	8
Brookfield Viscosity (cP)		-

* Actual parameters can vary between manufacturers and regions.

PACKAGE

** Mechanical Stability Time normally stabilizes within 21 days

205 kg/Drum

20 MT/Disposable or Non returnable flexi bags