



SPECIFICATION

MBTS (DM) Dibenzothiazole Disulfide

HS CODE - 38121000 | CAS NO - 120-78-5

NAME OF INDEX	FIRST GRADE
Appearance	White or light yellow powder
Melting point, ° C, min	166.0
Heating loss, %, max	0.40
Ash content, %, max	0.50
Residue(150µm),%,max	0.10

APPLICATION

The product is an accelerator of NR and SR. It has level and middle cure rate and higher Vulcanization temperature. It operates safely, disperses easily and does not contaminate, it is aging resistant. Mainly used in manufacture of tires, rubber goods. Accelerator MBTS works as plasticizer and delayed action activator in polychloroprene.

PACKAGE

In Knitted bag lined with plastic bag or kraft paper bag. 20kgs/bag or at buyer's request.