



## SPECIFICATION

### TSR 20

HS CODE - 40012200 | CAS NO - 9006-04-6

Standard Technical Data Sheet for TSR 20  
Raw Material - Coagulum

| Properties                             | Unit | *Limit |
|--|------|--------|
| Dirt Content - Max                     | % Wt | 0.16   |
| Ash Content - Max                      | % Wt | 0.80   |
| Volatile Matter - Max                  | % Wt | 0.80   |
| Nitrogen Content - Max                 | % Wt | 0.60   |
| Initial Wallace Plasticity (PO) - Min  |      | 30     |
| Plasticity Retention Index (PRI) - Min |      | 40     |

\*These figures represent standard limits. Actual parameters can vary between manufacturers and regions.

#### **Packing :**

35 kg/Bale

Loose bales, Shrink Wrapped Wooden/Disposable Plastic Pallet, Metal box.