



SPECIFICATION

THICK PALE CREPE - TPC 1

HS CODE - 40012920 | CAS NO - 9006-04-6

Average specifications - Thick Pale Crepe - TPC 1

Properties	Unit	*Avg Spec
Dirt Content - Max	% wt	0.02
Ash content - Max	% wt	0.2
Volatile Matter - Max	% wt	0.5
Nitrogen Content - Max	% wt	0.4
Initial Wallace Plasticity (PO)		40-60
Plasticity Retention Index (PRI)		60-75
Mooney Viscosity (ML, 1 + 4 at 100°C)		75-85
Lovibond Colour		1.5 - 2

Latex crepe is sold on visual grading.

*These figures represents Average Specification. Actual parameters can differ.

Packing :

25 kg/Bale

Loose bales, Shrink Wrapped Wooden/Disposable Plastic Pallet, Metal box.